

AstorLite® J223
Candle Wax & Additives
Product Data Sheet

Product Description	AstorLite® J223 is our newest jar candle wax formulation designed specifically to enhance both hot and cold fragrance throw. The wax performs best when poured at 145-155° F into a heated container		
Typical Properties and Characteristics	Test Description	ASTM Method	Typical
	Congealing Point	(ASTM D-938)	---
	Needle Penetration @ 77°F	(ASTM D-1321)	---
	Drop Melting Point	(ASTM D-127)	---
	Color (Saybolt)	(ASTM D-156)	---
			120 - 128°F
			96 – 120 dmm
			124-132 °F
			+ 8 MIN
Product Form and Packaging	AstorLite® J223 is offered in bulk liquid tank cars/tank trucks, and in slabs of approx. 10 lbs. Packed in 50 lb. boxes.		
Health & Safety	See MSDS		
Main Features and Benefits	<p>AstorLite® J223 is a container wax blend that exhibits the following qualities:</p> <ol style="list-style-type: none"> 1. It has excellent adherence to container sides 2. It is a single fill wax when poured at 145-155 degrees F 3. It can hold 8% to 10% fragrance 4. With the proper wick it has a 3.5" plus melt pool 5. The scent throw both cold and hot is excellent 6. AstorLite® J223 is opaque which allows brighter colors with less dye 		
Applications	Jar / Container Candle		
Offices	<p>Americas Honeywell Specialty Wax & Additives Mail Stop: Sol-3 101 Columbia Rd Morristown, NJ 07962</p> <p>Toll Free: 1-800-421-4929 Fax: 973-455-6154 Email: astorlite@honeywell.com</p>	<p>Europe / Middle East / Africa Honeywell Specialty Wax & Additives Hutte-60 B-4700 Eupen Belgium Telephone: 32-87-59-81-59</p> <p>Fax: 32-87-74-36-70 Email: astorlite@honeywell.com</p>	<p>Asia / Australasia Honeywell Pte Ltd 17 Changi Business Park Central 1 Honeywell Building Singapore 486073</p> <p>Telephone: 65-355-2828 Fax: 65-445-3033 Email: astorlite@honeywell.com</p>
Website	www.astorlite.com		

The information contained herein is, to our best knowledge, true and accurate, but all recommendations or suggestions are made without guarantee, since the conditions of use are beyond our control. There is no implied warranty of merchantability or fitness for purpose of the product or products described herein. In submitting this information, no liability is assumed or license or other rights express or implied given with respect to any existing or pending patent, patent applications or trademarks. The observance of all legal regulations and patents is the responsibility of the user.

